

X-ray and neutron diffraction on laser heated levitated samples successes and challenges

Sergey Vshakov
Alfred J. Pavlik
Alexandra Navrotsky



Richard J. K. Weber




Chris J. Benmore



Joerg C. Neuefeind




High temperature ceramics for aerospace and nuclear applications



MOTIVATION

Calculation of Phase Diagrams (CALPHAD) methods rely on thermodynamic data for compounds and their alloys / solid solutions




FactSage
MTDATA,
PANDAT,
MatCalc
JMatPro
ThermoCalc

MOTIVATION


Thermodynamic data from High Pressure X-ray diffraction

- ∅ Molar volumes as a function of temperature
- ∅ ΔV for solid state phase transitions
- ∅ ΔS_c for order-disorder transitions
- ∅ *In situ* phase diagram determination

MOTIVATION



Phase transitions in RE_2O_3




NSF DMR 1506229
Phase Transitions
in RE_2O_3 above 2000°C

Aerodynamic levitators with laser heating

APS 4D-D

SNS NOMAD BL1B



Chris Benmore


Richard Weber

Joerg Neufeind

METHOD

Aerodynamic levitators with laser heating

APS 6D-D



SNS NOMAD BL1B



Samples preparation



Powder melting



Levitation



Microprobe




Er_2O_3




Nd_2O_3

XRD data collection

APS 6-ID-D



CO₂ laser
10.6 μm





6 seconds collection

0.1 s exposure time
60 summed exposures

Cubic ZrO₂
T app = 2900
a = 5.283 Å

ND data collection



SNS NOMAD BL1B

Levitated V_2O_3 at RT
30 minutes


Data Processing

- ∅ Calibration at RT for every levitating bead
- ∅ Integration with FIT2D, refinement with GSAS/ExpGUI, FullProf/GSASII
- ∅ Le Bail refinement of cell parameters for high temperature H phases La_2O_3 , YEr_2O_3 , Ho_2O_3
- ∅ Refinement of room temperature structures on levitated samples to validate the method

ND of levitated Zr_2O_7 at RT,
 BANK 3, Rietveld fit


χ^2 2.75
 R_{wp} 4.8%
 R_F^2 4.3 %

a 10.8133(3)
 x(O) 0.3305 (1)
 $100 \cdot U_{50}$ Å
 La 0.65(4)
 Zr 0.34(4)
 O 0.84(3)
 0.10(3)



Scaling: 0.5(10.0X) 1.5(2.0X)

Results from 3 days of diffraction experiment on levitator at APS (June 17, 2011)





- ∅ Y₂O₃ transforms in-type before melting and O₂. Volume reduction on H phase transition was refined.
- ∅ Pyrochlore structure of Zr₂O₇ persists to the melting temperature. Thermal expansion was used to validate high temperature calculations.
- ∅ Thermal expansion of Dy₂ZrO₂ DF solid solutions and site occupancies pyrochlore DF phase transition in Zr₂O₇ were refined.

Maram PS, Ushakov SV, Weber RJ, Benmore CJ, & Navrotsky A (2015) *Am. Ceram. Soc.* 98(4), 1292

Hong Q-J, Ushakov SV, Navrotsky A, & van de Walle A (2015) *Acta Mater.* 84, 275


Ushakov SV & Navrotsky A (2012), *Am. Ceram. Soc.* 95, 1463

Thermal expansion of type RE_2O_3 in Oxygen flow





C-H premelting phase transitions in O_3RE

H-type Z=1





Y_2O_3	8V	-3.1%
Er_2O_3	8V	-3.4%
Ho_2O_3	8V	-3.9%



C-type Z=16

Pre-melting C-H phase transition in O_3RE in Ar

Neutron Diffraction results (Aug 23 2014)



Ushakov S. V., Navrotsky A., Weber, R. J. K. and Neuefeind J. C. (2015), Structure and Thermal Expansion of YSZ and $\text{La}_2\text{Zr}_2\text{O}_7$ Above 1500°C from Neutron Diffraction on Levitated Samples. J. Am. Ceram. Soc. 98: 3398

Conclusion

Refinement of high temperature structures is possible from X-ray and neutron diffraction on laser heated levitated samples using existing instruments at APS 4D-D and SNS NOMAD*

*Thermal gradient of $\sim 150^\circ\text{C}/\mu\text{m}$ in diffraction volume

UC Davis workshop on

Structure and

Thermodynamics of oxides at

High Temperature

October 1-21, 2016

(before MS&T 2016 ACS 118th meeting in Salt Lake City)

Confirmed Invited speakers:


Dario Manara, ITU

Elizabeth Opila, University of Virginia

Richard Weber, MDI

Lawrie Skinner, Stony Brook

<http://thermo.ucdavis.edu>



Questions ?